Insulated Panels
Australia

K-Roc® Firemaster Ultima Wall Panel
K-Roc® Firemaster Ultima Plus Wall Panel
Product Data Sheet

Building smarter with K-Roc®









THE K-ROC® ULTIMA RANGE IS DESIGNED FOR APPLICATIONS WITH FIRE RESISTANCE REQUIREMENTS

ACHIEVES UP TO FRL -/240/180*

FIRE-RESISTANCE LEVEL TESTED TO AS 1530.4 2014

*THE FIRE RESISTANCE RATING IS DEPENDENT ON THE PANEL THICKNESS USED, PANEL ORIENTATION, DIRECTION OF FIRE EXPOSURE AND THE MAXIMUM DISTANCE BETWEEN SUPPORTS

Product Data

Product Overview

These products are designed for use in applications where fire resistance levels are required.

K-Roc® Firemaster Ultima Wall Panel & K-Roc® Firemaster Ultima Plus Wall Panel are bonded laminated materials. They achieve the necessary fire test results, as required by clause C2D10 (6)(g) of the National Construction Code (NCC). Therefore, they can be used wherever a non-combustible material is required by the NCC.

Application

Ideally suited for the construction of non-load bearing internal walls with fire resistance requirements.

These insulated panels are ideal for use in food processing and storage applications, along with data centres, microelectronics and pharmaceutical facilities, where protected zones or clean rooms are often required.



Dimensions, Thermal Performance & Weight

Product	Cover width (mm)	Nominal Thickness (mm)	Product R-Value (m^2K/W) at 23°C	Product U-Value (m^2K/W) at 23°C	Total R-Value (m^2K/W)		Weight* (kg/m^2)
					Heat Flow Out (Winter)	Heat Flow In (Summer)	
K-Roc® Firemaster Ultima	1,100	150	4.25	0.24	4.55	4.25	27.50
		175	4.95	0.20	5.30	4.95	30.50
		200	5.65	0.18	6.00	5.65	33.25
	1,200	150	4.25	0.24	4.55	4.25	25.75
		175	4.95	0.20	5.30	4.95	28.75
		200	5.65	0.18	6.00	5.65	31.50
K-Roc® Firemaster Ultima Plus	1,100	100	2.80	0.35	3.10	2.90	19.25
		120	3.40	0.29	3.65	3.45	21.50
		150	4.25	0.24	4.55	4.25	25.00
	1,200	100	2.80	0.35	3.10	2.90	19.75
		120	3.40	0.29	3.65	3.45	22.25
		150	4.25	0.24	4.55	4.25	25.75

The R-Values shown are Total R-Values for the building element as required by the Energy Provisions of the National Construction Code, calculated in accordance with AS/NZS 4859.2: 2018.

K-Roc® Firemaster Ultima Wall Panel & K-Roc® Firemaster Ultima Plus Wall Panel are manufactured, tested and packaged in conformance with AS/NZS 4859.1: 2018.

Declared Product R-Value is calculated in accordance with AS/NZS 4859.1: 2018 as required for compliance to the National Construction Code.

* Actual weight subject to vary ± 10% due to manufacturing and raw material tolerances.

Cover Widths

Standard cover widths	1,100 mm and 1,200 mm

Fixing Method

Through-fix.

† Fire-resistance Levels (FRL) are subject to certain details including panel thickness, width, orientation, distance between supports and method of assembly.

Product Data

Available Lengths

Standard lengths: 2.0 m - 12.0 m.
Export of Australia / sea freight to WA: 11.8 m.

Core thickness (mm)	Core thickness (mm)	Minimum length (m)	Maximum length (m)
K-Roc® Firemaster Ultima	150	2.0	12.0
	175		
	200		
K-Roc® Firemaster Ultima Plus	100	2.0	10.0
	120	2.0	12.0
	150		

Note: Additional costs and transport restrictions may apply for non-standard lengths.

Certification and Testing

Combustibility

K-Roc® Firemaster Ultima Wall Panel & K-Roc® Firemaster Ultima Plus Wall Panel are bonded laminated materials. They achieve the following fire test results, as required by clause C2D10 (6)(g) of the National Construction Code (NCC). Therefore, it can be used wherever a non-combustible material is required by the NCC.

Product	Test Method	Result
Mineral wool core	AS 1530.1 1994 (R2016) Combustibility test for materials	Not deemed combustible
Panel steel skin (uncoated)		Not deemed combustible

Test	Test Method	Result
Ignitability	AS/NZS: 1530.3: 1999	Ignitability Index: 0
Flame Spread		Spread of Flame Index: 0
Heat Release		Heat Evolved Index: 0
Smoke Release		Smoke Developed Index: ≤ 3

There are two factory-applied adhesive layers applied during the manufacture of the product. Each adhesive layer does not exceed 1 mm in thickness and the total thickness of the adhesive layers does not exceed 2 mm in thickness.

Test	Test Method	Result
NCC Group Number in accordance with AS 5637.1: 2015	AS 5637.1: 2015 / ISO 9705 2003 (R2016)	Group 1
Smoke Growth Rate Index (SMOGRA$_{RC}$) (m^2/S^2 x 1000)		< 100

Fire Resistance

K-Roc® Firemaster Ultima Wall Panel & K-Roc® Firemaster Ultima Plus Wall Panel are tested in accordance with AS 1530.4 2014. Fire-resistance Levels (FRL) are subject to certain details including panel thickness, width, orientation, distance between supports and method of assembly.

Solutions for doors and penetrations in fire-rated applications are available (doors limited to panel thicknesses ≥ 150 mm). Permissible configurations and their installation requirements are to be verified with the passive fire protection supplier.

Please contact Technical Services for the specific information on the fire-resistance levels available and the installation detail required.

K-Roc® Firemaster Ultima Wall Panel				
Panel Thickness (mm)	Panel Orientation	Stitching Required	Maximum FRL distance between supports	FRL
150	Vertical	Not required	7.5 m	**-/90/90**
150	Vertical	Not required	6.0 m	**-/120/120**
175, 200	Vertical	Not required	6.0 m	**-/240/180**
175, 200	Vertical	Not required	7.5 m	**-/180/180**

K-Roc® Firemaster Ultima Plus Wall Panel				
Panel Thickness (mm)	Panel Orientation	Stitching Required	Maximum FRL distance between supports	FRL
100	Vertical	Not required	7.5 m	**-/120/120**
100	Vertical	Not required	3.0 m	**-/180/120**
120, 150	Vertical	Not required	7.5 m	**-/180/180**
150	Horizontal	Not required	7.5 m	**-/120/120**
150	Horizontal	Not required	6.0 m	**-/180/180**

Notes: Tables must be read in conjunction with relevant fire resistance report. Tables provided above applies to the wall system exposed to fire from either direction, but not simultaneously. Maximum FRL distance between supports are confirming the maximum from a fire resistance perspective, additional loads anticipated from wind loads or other may result in reductions to maximum allowable distance between supports. Structure has not been included in the tables.

Product Data

Profiles

External Profile: Flat.
Internal Profile: Flat.

Flat / Flat



Product Tolerances

Product tolerances in accordance with EN 14509: 2013.

Length (≤ 3 m)	± 5 mm
Length (> 3 m)	± 10 mm
Width	± 2 mm
Thickness (≤ 100 mm)	± 2 mm
Thickness (> 100 mm)	± 2 %
Squareness	≤ 0.6% of width
Flatness* (L = 200 mm)	0.6 mm
Flatness* (L = 400 mm)	1.0 mm
Flatness* (L = 700 mm)	1.5 mm
Bowing	2 mm per metre length up to max. 20 mm

* Flatness shall be measured at least 100 mm from the edge of panel and 200 mm from the end of panel.

Insulation Core

K-Roc® Firemaster Ultima Wall Panel & K-Roc® Firemaster Ultima Plus Wall Panel are manufactured with a 115 kg/m³ density mineral wool insulation core with a tolerance of ± 10%.

Product Data

Materials

External Sheet

- Substrate to be G300S steel with Z275 metallic coating in accordance with AS 1397: 2021.
- Paint coating in accordance with AS / NZS 2728: 2013.

Internal Liner

- Substrate to be G300S steel with Z275 metallic coating in accordance with AS 1397: 2021.
- Paint coating in accordance with AS / NZS 2728: 2013.

Security. Built in.

K-Roc® panels engineered for high-security environments.

Speak to Kingspan about our alternative material offering, proven across demanding security applications where durability, resilience and long-term performance are critical.

Available on one or both sides of K-Roc® Firemaster Ultima Wall Panels & K-Roc® Firemaster Ultima Plus Wall Panels, in our standard paint coating offer.

Contact Kingspan to discuss additional coating options and project-specific requirements.

Coatings

External Sheet and Internal Liner

- Standard: Coolroom White. Other colours are available on request. Please contact your local area sales manager for further information.

Other Internal Coating Options*

- Kingspan AQUA*safe* 25 and Kingspan AQUA*safe* 55: The coating has been developed for use as the internal lining of insulated panels to suit high humidity internal environments.

* Please contact Technical Services for further information regarding substrates and coatings. Internal coatings subject to availability and panel cover width.

Load / Span

Specific span performance information can be provided by Kingspan Technical Services on a project-by-project basis.

Quality and Durability

K-Roc® Firemaster Ultima Wall Panel & K-Roc® Firemaster Ultima Plus Wall Panel are manufactured from high quality materials using state-of-the-art production equipment to rigorous quality control standards, complying with ISO 9001 standard, ensuring long-term reliability and service life. The panels are also being manufactured under Environmental Management System Certification ISO 14001, Occupational Health and Safety Certification ISO 45001 and Compliance Management Systems ISO 37301.

Packaging

K-Roc® Firemaster Ultima Wall Panel & K-Roc® Firemaster Ultima Plus Wall Panel are stacked horizontally. The entire length of the pack of panels is shrink wrapped. The number of panels in each pack depends on panel length, weight, and thickness. Typical pack height is 1,200 mm. Additional corner and edge protection for container transport is offered upon request.

Delivery

All deliveries (unless indicated otherwise) are by flatbed road transport to project site. Off loading is the responsibility of the client. Export orders are transported in shipping containers. WA orders are transported in shipping containers, unless road freight is opted for.

Site Installation Procedure

Site assembly instructions are available from Technical Services. Kingspan recommend that the appointed contractor attend the product installation training course prior to installation, which is provided by Kingspan Field Services.

Accreditations

FPA AUSTRALIA GOLD MEMBER Fire Protection Association Australia

Green Building Council Australia Member 2025–2026

100% We buy GreenPower®

British Assessment Bureau UKAS MANAGEMENT SYSTEMS 8289 ISO 9001 QUALITY MANAGEMENT

British Assessment Bureau UKAS MANAGEMENT SYSTEMS 8289 ISO 14001 ENVIRONMENTAL MANAGEMENT

British Assessment Bureau UKAS MANAGEMENT SYSTEMS 8289 ISO 45001 HEALTH & SAFETY MANAGEMENT









Locally made for maximum efficiency.
St Marys, Sydney.

Contact Details

Australia

Kingspan Insulated Panels Pty Ltd
38-52 Dunheved Circuit | St Marys
NSW 2760 Australia

T: +61 (02) 8889 3000
F: +61 (02) 8889 3099
E: info@kingspanpanels.com.au
kingspanpanels.com.au

Please scan for the most up to date version of this Product Data Sheet.

For the product offering in other markets please contact your local sales representative or visit www.kingspanpanels.com

Care has been taken to ensure that the contents of this publication are accurate, but Kingspan Limited and its subsidiary companies do not accept responsibility for errors or for information that is found to be misleading. Suggestions for, or description of, the end use or application of products or methods of working are for information only and Kingspan Limited and its subsidiaries accept no liability in respect thereof.

Fifth Issue | 15/07/2026